

ResMart ABS VH-0800 NT - Flame retardant ABS for injection molding applications

Technical Data Sheet Properties

Physical Property	Value	Test Method
Specific Gravity	1.17	ASTM D 792
Melt Flow Rate @ 200°C - 5Kg	6.0 g/10 min	ASTM D1238
Mold Shrinkage	0.31 - 0.37 %	ASTM D 955

Mechanical Property	Value	Test Method
Tensile Strength	6000 psi	ASTM D 638
Tensile Strain at Break	24 %	ASTM D638
Tensile Modulus	200000 psi	ASTM D 638
Flexural Strength	8800 psi	ASTM D 790
Flexural Modulus	310000 psi	ASTM D 790
Notched Izod Impact Strength	4.3 ft-lb/in.	ASTM D256
Rockwell Hardness (R-Scale)	107	ASTM D 785

Thermal Property	Value	Test Method
HDT (264 psi) Unannealed	158 °F	ASTM D 648
HDT (66 psi) Unannealed	196 °F	ASTM D 648
Vicat Softening Temperature	86 °C	ISO 306
Flame Rating	V-0 @ 1.5mm	UL 94

Regulatory Compliance	Value
RoHS Compliance	Yes

Processing Guidelines	Value
Drying Temperature	180 °F
Drying Time	2 - 4 Hours
Suggested Max Moisture	0.05 %
Melt Temperature	380 - 430 °F
Mold Temperature	100 - 180 °F

The information provided on this datasheet should only be used as a guideline. Actual lot to lot values will vary.

Disclaimer: No information supplied by ResMart LLC constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon ResMart LLC or other customer experience. ResMart LLC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.